

1500 St. Clair Avenue Kent, Ohio 44240-0668 Phone: (330) 673-1011 Toll Free: (800) 331-4762 Fax: (330) 673-1351

Technical Data Sheet K2200 Thermoplastic Elastomer

KEP Thermoplastics have been used by many of the world's leading medical device and Food & Beverage companies for over 20 years. Thermoplastic Elastomers offer a wide range of choices, providing specific properties, and functional benefits for new and existing applications. Kent's FDA-registered extrusion facility is maintained and adheres to ISO9000 and GMP guidelines. State of the art in-line laser gauges monitor precise and strict dimensional tolerances.

Typical Physical Properties

Properties based on injection molded samples

ASTM D-2240	ASTM D-412	ASTM D-412	ASTM D-412	ASTM D-412
Durometer (shore A)	Tensile @ Break	Elongation	100% Modulus	300% Modulus
66	950 psi (6.6 MPa)	590%	490 psi (3.4 MPa)	670 psi (4.6 MPa)

Dimensions are controlled by in-line laser gauges. Products are made in the USA.

Key Features

Operating Temp. -40 to 195°F (-40 to 91°C)

Color: Translucent Resistant to Ozone Bondable to Polypropylene
Natural Colors are available Compatible: fatty food use*

Natural Finish: Gloss Compatible: hot liquid use*
Other surface finishes available Excellent colorability

her surface finishes available Excellent colorability
Good memory (12%)

Dimensionally stable

Biocompatibility

Meets FDA food grade requirements

Regulatory Compliance

DEHP free
Phthalate free
BPA Free
No sources of BSE or TSE

The buyer must perform all tests necessary to confirm whether the product and its performance and qualities are suitable for the intended application. Final determination of fitness of the product for the intended application is the buyer's responsibility. Kent Elastomer shall not be liable for any misuse or misapplication of its products.

Document control: LC-1.K2200 Revision: 050119 Printed Copies are NOT CONTROLLED

^{*}Use is related to the FDA status of the material (see applicable CFR section) and the end use of the application. The end use needs to be evaluated to determine if it is acceptable for fatty food and/or hot liquid use.